

SPECIFICATION

BE IT KNOWN THAT WE, TAKASHI NAKAMURA, TETSUYA KUNISAWA and TOSHIRO MATSUO, all residing at c/o Sumitomo Rubber Industries, Ltd., 6-9, 3-chome, Wakinohama-cho, Chuo-ku, Kobe-shi, Hyogo-ken, Japan, subjects of Japan, have invented certain new and useful improvements in

RUBBER COMPOSITION FOR SIDEWALL AND PNEUMATIC TIRE USING THE SAME

of which the following is a specification:-

RUBBER COMPOSITION FOR SIDEWALL AND PNEUMATIC TIRE
USING THE SAME

BACKGROUND OF THE INVENTION

The present invention relates to a rubber composition for a sidewall of an automobile tire and a pneumatic tire using the same.

In order to reduce rolling resistance of a tire, a tire can be
5 made lightweight. The conventional method for obtaining a lightweight
tire is the method of reducing the amount of rubber that forms the tire.
However, durability of a tire is decreased by this method. Also, because
a small amount of rubber is used, stiffness of the tire and steering
stability tend to decrease. When the amount of the filler in a rubber
10 composition is reduced, rolling resistance can be reduced, but
reinforcement properties of the rubber decrease.

It is known that both improvement in fatigue of the rubber
and reduced heat generation can be obtained, when a thermoplastic
elastomer or an olefin resin is compounded to the rubber component as
15 a reinforcing agent of fiber (see JP-A-7-309974, JP-A-7-309975). It is
also known that rubber having high elasticity and high stiffness can be
obtained and destruction properties can be improved, by compounding
polyolefin such as polyethylene (see JP-A-9-272307, JP-A-10-315717,
JP-A-10-195249). However, in these methods, the kneading
20 temperature of the rubber composition is high and exceeds the melting
point of polyolefin. As a result, dispersion of the compounded
polyolefin is insufficient. Consequently, steering stability is insufficient
and a lightweight tire cannot be prepared. In addition, the polyolefin
powder is poor in adhesion with diene rubber and is known to easily

become the destruction point.

Also, known is the method of burying a thermoplastic elastomer composition in a sidewall, in order to reduce road noise of a tire (see JP-A-9-300921). However, according to this method, rolling
5 resistance cannot be reduced while maintaining steering stability.

SUMMARY OF THE INVENTION

The present invention aims to obtain a lightweight tire without decreasing durability and to reduce rolling resistance and
10 improve steering stability of the tire.

That is, the present invention relates to a rubber composition for a sidewall comprising 20 to 70 parts by weight of an inorganic filler, and 5 to 35 parts by weight of polypropylene powder, based on 100 parts by weight of a rubber component, which satisfies the following equation:

15

$$\begin{aligned} &(\text{amount of polypropylene powder}) \leq \\ &(\text{amount of inorganic filler} + \text{amount of polypropylene powder})/2. \end{aligned}$$

The particle size of the polypropylene powder is preferably at
20 most 500 μm .

The rubber component preferably contains at most 70 parts by weight of at least one rubber selected from the group consisting of butadiene rubber, isoprene rubber, butyl rubber and halogenated butyl rubber.

25 The present invention also relates to a pneumatic tire comprising the rubber composition for a sidewall.

DETAILED DESCRIPTION

The rubber composition for a sidewall of the present invention contains a rubber component, an inorganic filler and polypropylene powder.

5 The rubber composition for a sidewall of the present invention contains diene rubber such as natural rubber (NR), butadiene rubber (BR), isoprene rubber (IR), butyl rubber (IIR), halogenated butyl rubber, styrene-butadiene rubber (SBR) and nitrile butadiene rubber (NBR) as a rubber component. The amount of NR in 100 parts of the
10 rubber component is preferably 30 to 100 parts by weight, more preferably 40 to 70 parts by weight. Also, as a rubber component other than NR, 0 to 70 parts by weight of at least one rubber selected from the group consisting of butadiene rubber, isoprene rubber, butyl rubber and halogenated butyl rubber is preferably contained. When the amount of
15 the rubber component other NR is more than 70 parts by weight, processability and workability tend to decrease. The rubber component, which is at least one rubber selected from the group consisting of butadiene rubber, isoprene rubber, butyl rubber and halogenated butyl rubber, is preferably contained in the rubber composition for a sidewall of
20 the present invention, in view of improvement in resistance to flex cracking and crack growth.

 The rubber composition for a sidewall of the present invention contains carbon black and/or silica as an inorganic filler. The kind of carbon black is not particularly limited and examples thereof
25 are HAF, ISAF and SAF. Also, the kind of silica is not particularly limited and examples thereof are dry silica (silicic anhydride) and wet silica (hydrous silica). The amount of carbon black and/or silica as the

inorganic filler is 20 to 70 parts by weight, preferably 35 to 70 parts by weight, more preferably 40 to 60 parts by weight, based on 100 parts by weight of the rubber component. When the amount of carbon black and/or silica is less than 20 parts by weight, reinforcement properties
5 decrease significantly and when the amount is more than 70 parts by weight, rolling resistance becomes poor, thus being unfavorable.

The rubber composition for a sidewall of the present invention contains polypropylene (hereinafter referred to as PP) powder. The PP powder can be powder obtained by drying after polymerization or
10 by freezing and pulverizing the powder dried after polymerization. The process for preparing the PP powder is not particularly limited. The amount of the PP powder is 5 to 35 parts by weight, preferably 10 to 20 parts by weight, based on 100 parts by weight of the rubber component. When the amount of PP powder is less than 5 parts by weight, a
15 lightweight tire cannot be achieved and steering stability cannot be improved. When the amount of PP powder is more than 35 parts by weight, the rubber becomes brittle and strength and durability decrease. The PP powder used in the present invention is powder having small particle size. The particle size of the PP powder is preferably at most
20 500 μm , more preferably 1 to 300 μm , further preferably 1 to 100 μm . When the particle size of the PP powder is more than 500 μm , the PP powder does not disperse in the rubber and remains as foreign material, decreasing durability, thus being unfavorable. Also, from the viewpoint of high melting point and hardness, the PP powder preferably has high
25 crystallinity.

When mixing the PP powder with the rubber component, the kneading temperature is preferably 110 to 165°C, more preferably 110 to

160°C. When kneading is conducted at a temperature higher than 165°C, the PP powder melts and phase conversion occurs. As a result, the rubber does not come together and sheet processability tends to decrease. When kneading is conducted at a temperature lower than 110°C, kneading is often insufficient and the dispersion condition becomes poor, thus being unfavorable.

The rubber composition for a sidewall of the present invention satisfies the following equation:

$$\frac{\text{(amount of polypropylene powder)}}{\text{(amount of inorganic filler + amount of polypropylene powder)}} \leq \frac{1}{2}$$

The (amount of polypropylene powder) is preferably 20 to 40 % of the (amount of inorganic filler + amount of polypropylene powder). When the (amount of polypropylene powder) is more than 1/2 of the (amount of inorganic filler + amount of polypropylene powder), rubber hardness decreases and durability tends to become poor.

In the rubber composition for a sidewall of the present invention, process oil (such as paraffin process oil, naphthene process oil and aromatic process oil) can be compounded. The amount of the process oil is preferably 1 to 40 parts by weight, more preferably 1 to 20 parts by weight, based on 100 parts by weight of the rubber component. When the amount of process oil is less than 1 part by weight, processability tends to become poor and when the amount of process oil is more than 40 parts by weight, hardness of the rubber decreases and steering stability tends to become poor.

Furthermore, a silane coupling agent can be compounded

together with silica in the rubber composition for a sidewall of the present invention. Also, besides the rubber component, the inorganic filler and PP powder, compounding agents that are usually used in a rubber composition can be compounded accordingly, such as a wax, an antioxidant, stearic acid, zinc oxide, a process oil, a vulcanizing agent and a vulcanization accelerator.

The rubber composition for a sidewall of the present invention is obtained by kneading the rubber component, inorganic filler comprising carbon black and/or silica, PP powder and other compounding agents when necessary, using the usual processing apparatus such as a roll, a banbury mixer and a kneader.

The rubber composition of the present invention can be applied to all areas where a composition of high hardness is required, but is most effective as a sidewall composition, which is required to have properties such as high hardness and high stiffness in order to maintain durability.

The tire of the present invention is prepared by the usual method using the rubber composition for a sidewall.

The present invention is explained in detail based on Examples below but not limited thereto.

EXAMPLES 1 to 3 and COMPARATIVE EXAMPLES 1 to 3

The components other than sulfur and the vulcanization accelerator were kneaded using a 1.7 L banbury made by Kobe Steel, Ltd. Then, sulfur and the vulcanization accelerator were added to the obtained kneaded article and kneading was conducted with a twin-screw roller. The obtained mixture was vulcanized at 150°C for 30 minutes to

obtain a rubber composition for a sidewall. Each component used in Examples and Comparative Examples is shown in Table 1. The PP powder that was used is H-700 available from Idemitsu Petrochemical Co., Ltd., having a particle size of 70 μm and a melting point of 165°C.

- 5 In Examples and Comparative Examples, a tire was prepared using PP powder in the sidewall, but the present invention is not limited thereto.

TABLE 1

Component	
Diene Rubber	Natural rubber (RSS #3 grade) Butadiene rubber (available from Ube Industries, Ltd.)
Carbon Black	N550 (available from Showa Cabot Co., Ltd.)
Process Oil	Diana Process Oil PS32 (available from Idemitsu Kosan Co., Ltd.)
Wax	SUNNOC WAX (available from Ouchi Shinko Chemical Industrial Co., Ltd.)
Antioxidant	SANTOFLEX 13 (available from FLEXSYS CO.)
Stearic Acid	KIRI (available from NOF Corporation)
Zinc Oxide	Zinc Oxide Type 2 (available from Mitsui Mining and Smelting Co., Ltd.)
PP Powder	H-700 (available from Idemitsu Petrochemical Co., Ltd.)
Sulfur	Insoluble Sulfur (available from Nippon Kanryu Industry Co., Ltd.)
Vulcanization Accelerator	Nocceler CZ (available from Ouchi Shinko Chemical Industrial Co., Ltd.)

Measurement

Hardness (JIS-A)

- 5 Hardness of the prepared rubber composition for a sidewall was measured at 25°C using a JIS-A hardness meter.

Viscoelasticity

Complex modulus (E^*) and loss tangent ($\tan\delta$) at 60°C were measured under a frequency of 10 Hz, initial strain of 10 % and dynamic

strain of 2 % using VES-F-3 made by Iwamoto Corporation. The larger the E^* value is the higher the stiffness and the more superior the steering stability. Less heat generation occurs the smaller $\tan\delta$ value is.

5 Tensile test

Tensile test of the prepared rubber composition for a sidewall was conducted according to JIS-K6251 using a type 3 dumbbell and tensile strength at break (TB) and elongation at break (EB) were measured. The larger the obtained number value is the more favorable the rubber strength.

Steering stability and riding comfort

A 195/60R15 size tire was prepared by the usual method and sensory evaluation was conducted on a test course using a normal automobile to which the above tire was mounted.

15 Lightweight tire

The weight of the prepared tire was measured under windless conditions using a scale. With consideration to the margin of error, a tire of the same standard was weighed under conditions of $N =$ at least 3 and the average value was assumed to be the tire weight. The value shown in Table 2 demonstrates the degree to which the tire was made lightweight in comparison to the standard tire.

TABLE 2

	Ex.			Com. Ex.		
	1	2	3	1	2	3
Composition (parts by weight)						
Rubber Component						
NR	50	50	50	50	50	50
BR	50	50	50	50	50	50
Carbon Black	45	35	25	50	42.5	10
Process Oil	5	5	5	5	5	5
Wax	2	2	2	2	2	2
Antioxidant	3	3	3	3	3	3
Stearic Acid	2	2	2	2	2	2
Zinc Oxide	3	3	3	3	3	3
PP Powder	5	15	25	0	2.5	40
Sulfur	1.5	1.5	1.5	1.5	1.5	1.5
Vulcanization Accelerator	1	1	1	1	1	1
Test						
Hs (JIS-A	51	53	55	50	50	60
VES						
E* (MPa)	4.5	5.2	5.7	3.7	3.9	6.2
tan δ (%)	0.16	0.14	0.10	0.17	0.17	0.09
Tensile						
TB (MPa)	17.8	18.6	20.1	16.6	16.8	24.3
EB (%)	488	462	459	635	559	388
Steering Stability	◎	◎	◎	○	○	◎
Riding Comfort	○	○	○	○	○	△
Lightweight Tire/g	38	80	180	standard	15	200

In Example 1, hardness and the E* value were high and steering stability was improved, in comparison to Comparative Example 1. Also, the obtained tire was lighter. On the other hand, in Comparative Example 2, hardness and the E* value were slightly higher, but the effects of improving steering stability and obtaining a lightweight tire were not achieved. In Comparative Example 3, the rubber strength decreased.

Usually, the specific gravity of polypropylene is at most 1 (0.91). On the other hand, the specific gravity of the rubber is at least 1. By compounding polypropylene powder having a low specific gravity to the rubber composition for a sidewall as in the present invention, a lightweight tire can be obtained.

According to the present invention, a lightweight tire can be obtained without decreasing durability and reduced rolling resistance and improved steering stability of the tire can be achieved.